


Product Dimensions and Weights

DIN 95 Specifications

Metric DIN 95 Slotted Oval Head Wood Screws



GAUGE										
No.	16	18	19	20	21	22	23			
D (mm)	2.5	3	3.5	4	4.5 5		6			
DC	4.7	5.6	6.5	7.5	8.3	9.2	11			
K	1.50	1.65	1.93	2.20	2.35	2.50	3.00			
n	0.6	0.8	0.8	1	1	1.2	1.6			
L (mm)	Weight (kg / 1000 pcs)									
10	0.38	0.64	0.84							
12	0.44	0.73	0.97	1.27						
16	0.56	0.92	1.22	1.58	1.89	2.29				
20	0.69	1.10	1.50	1.89	2.27	2.77				
25	0.84	1.35	1.79	2.27	2.76	3.37				
30	1.01	1.59	2.11	2.66	3.26	4.00				
35		1.82	2.44	3.05	3.75	4.56				
40		2.06	2.74	3.45	4.22	5.16	7.60			
45		2.29	3.06	3.78	4.73	5.75	8.45			
50		2.52	3.37	4.17	5.22	6.35	9.29			
60		2.98	3.68	5.04	6.20	7.57	11.00			
70		3.44	3.98	5.44	6.70	8.77	12.70			

All measurements are in mm

Aspen Fasteners 4807 Rockside Road, Suite 400, Independence, OH 44131 USA www.aspenfasteners.com | aspensales@aspenfasteners.com | 1-800-479-0056



Metric DIN 95 Oval (Raised Countersunk) Head Slotted Wood Screws are the preferred fasteners used to attach wood to wood or hardware to wood. The aggressive self tapping part thread with a sharp point allows for effective penetration and gripping in the wood to form strong joints. The oval heads are countersunk (cone shaped under the head) with a slightly rounded top. These are often used to attach finishing hardware (eg hinges) to wood. The slotted drive is a simple slot cut into the outer surface of the head for a flat blade slot screw driver. Aspen Fasteners offers over 500,000 unique fastener products from stock in inch and metric standard in a variety of materials and finishes. The following sizes DIN 95 Oval Head Slotted Wood Screws are available for immediate shipping from stock: Diameters ranging from M3 to M8 up to 100mm long in stainless steel A2 and A4. View parts by clicking on the following link: DIN 95 Oval Head Slotted Wood Screws

DIN (**D**eutsches Institut für **N**ormung - German Institute for Standardization) standards are issued for a variety of components including industrial fasteners as Metric DIN 95 Oval Head Slotted Wood Screws. The DIN standards remain common in Germany, Europe and globally even though the transition to ISO standards is taking place. DIN standards continue to be used for parts which do not have ISO equivalents or for which there is no need for standardization as DIN 95 Oval Head Slotted Wood Screws.

1) Mechanical properties of stainless steel for metric DIN 95 Oval Head Slotted Wood Screws

Stainless steels can be divided into three groups of steel - austenitic, ferritic and martensitic. Austenitic steel is by far the most common type (>90% of commercial fasteners). The steel groups and strength classes are designated by a four-digit sequence of letters and numbers (eg A2-70) as shown in the following table. DIN EN ISO 3506 governs screws and nuts made from stainless steel.

			Screws, Nuts and Bolts						
Steel group	Steel grade	Strength class	Tensile strength N/mm ²	Tensile strength PSI	Dia range	Nut Load N/mm²			
	A2 and A4	50	500	70,000	<=M39	500			
Austenitic		70	700	100,000	<=M20	700			
		80	800	118,000	<=M20	800			

The tensile stress is calculated with reference to the tensile stress area (see DIN EN ISO 3506-1979). Nuts to be paired with same grade of stainless steel screws



Steel group	Property Strength class	Made From	Characteristics
	50	A1, A2	Soft; cold worked, turned and soft pressed fasteners
Austenitic	70	A2, A4	Cold worked, normal strength formed fasteners
	80	A2, A4	Extreme cold worked, high strength, special applications

2) Chemical composition of stainless steel metric DIN 95 Oval Head Slotted Wood Screws

Grade	USA Grade	Material designation	Material no.	C %	Si ≤ %	Mn ≤ %	Cr %	Mo %	Ni %
A 2	304	X 5Cr Ni 1810	1.4301	≤ 0.07	1.0	2.0	17.5 to 19.5	ı	8.0 to 10.5
		X 2 Cr Ni 1811	1.4306	≤ 0.03	1.0	2.0	18.0 to 20.0	ı	10 to 12.0
		X 8 Cr Ni 19/10	1.4303	≤ 0.07	1.0	2.0	17.0 to 19.0	ı	11.0 to 13.0
A 4	316	X 5 Cr Ni Mo 1712	1.4401	≤ 0.07	1.0	2.0	16.5 to 18.5	2.0 to 2.5	10.0 to 13.0
		X 2 Cr Ni Mo 1712	1.4404	≤ 0.03	1.0	2.0	16.5 to 18.5	2.0 to 2.5	10 to 13



3) Chemical composition of steel metric DIN 95 Oval Head Slotted Wood Screws

PROPERTY CLASS		CHEM	ICAL COMP	TEMPERING			
	MATERIALANDTREATMENT	(Р	S	TEMPERING TEMP °C MIN.	
		min.	max.	max.	max.		
4.6, 4.8, 5.8, 6.8	Low or medium carbon steel	-	0.55	0.05	0.06	-	
8.8	Medium carbon steel quenched, tempered	0.25	0.55	0.04	0.05	425	
9.8	Medium carbon steel quenched, tempered	0.25	0.55	0.04	0.05	425	
10.9	10.9 Medium carbon steel additives e.g. boron, Mn, Cr or Alloy steel - quenched, tempered		0.55	0.04	0.05	425	
12.9	Alloy steel - quenched, tempered	0.20	0.50	0.035	0.035	380	

4) Mechanical properties of steel for metric DIN 95 Oval Head Slotted Wood Screws

		PROPERTY CLASS									
MECHANICAL PROPERTY							8.8				
			4.8	5.6	5.8	6.8	Up to M 16	Over M 16	9.8	10.9	12.9
Tensile Strength	nom.		400	5	00	600	800		900	1000	1200
(Rm, N/mm²)	m	in.	420	500	520	600	800	830	900	1040	1220
Vickers Hardness	min.		130	155	160	190	250	255	290	320	385
Vickers naturiess	max		250			320	336	360	380	435	
Brinell Hardness	min.		124	147	152	181	319	242	266	295	353
Dillell Haluless	max.		238			385	319	342	363	412	
	min.	HR	71	79	82	89			-		
Rockwell Hardness		HRC	-	-	-	-	20	23	28	32	39
Rockwell Haruress	HR			95	99			1			
	max.	HRC	-	-	-	-	32	34	37	39	44
Yield Stress ReL.	nom.		320	300	400	480	-				
N/mm²	m	in.	340	300	420	480	-				
Stress at permanent	nom.				-		6	640 720 900 10			1080
set limit N/mm²	min.				-		640 660 720 940 1100			1100	



Disclaimer

Dimensional data and technical information for Metric DIN 95 Oval Head Slotted Wood Screws was obtained from publicly available sources and not acquired through standards agencies. It has been completed and compiled for reference purposes only; where discrepancies are found they are subject to change without notice. Aspen Fasteners makes no warranties or representations regarding the accuracy and validity of the compiled information and data. Contact the relevant standards authorities for accurate and detailed information.